

# Syntech Epox Timber



**CARINSKI KOD:** 3907 3000

**KOMPONENTE:** Dvokomponentna

**IZGLED:** Tekućina + Tekućina

**DOSTUPNE BOJE:** Trasparente

**PAKIRANJA I DIMENZIJE:** Secchio 0.7 kg [A] - Secchio 3.5 kg [A] - Secchio 0.3 kg [B] - Secchio 1.5 kg [B] - Kit: 1 Secchio 0.7 kg [A] + 1 Secchio 0.3 kg [B] - Kit: 1 Secchio 3.5 kg [A] + 1 Secchio 1.5 kg [B]

## DOPUŠTENE PODLOGE

Wood


## METODE PRIMJENE

Colatura


## ČIŠĆENJE ALATA


Voda


## OSNOVNE ZNAČAJKE


 Bez otapala

 Max. preporučena debljina: 10 cm

 Otporno na UV-zrake


 Temperatura na kojoj se upotrebljava: +20 / +30 °C


 Use wearing protective gloves

 Gustoća: 1.07 ± 0.02 kg/l

**A:B** Mixing ratio: 3:1 \_

 Rok trajanja: 12 mjeseci

 Use wearing protective glasses

 Vrijeme za obradu nakon miješanja: (\*) 200 min



## TEHNIČKE SPECIFIKACIJE

Shore D EN ISO 868  
Hardness **80**

Tlačna čvrstoća **80 MPa**

\*  
Complete hardening at 20°C **7 gg**

Adhesion to substrate **> 4 MPa**

\*  
Time before second coat at 20°C **4 - 5 h**

A+B  
Viscosity **1000 - 1100 mPas**

max  
Working temperature **57 °C**

Reaction to fire **BFL s1**

ASTM D 638  
Longitudinal elongation at break **3.2 ± 0.2 %**


\*  
Touch hardening at 20°C **8 h**

(\*) Times are reduced as mass, thickness and temperature increase.

## SKLADIŠTENJE I ČUVANJE

Protect from freezing. Čuvati proizvod u originalnom pakiranju, u dobro prozračenom i suhom prostoru, izbjegavajući mraz i izravno sunčevo svjetlo. Neprimjereno skladištenje proizvoda može imati za posljedicu gubitak reološkog svojstva. Zaštititi proizvod od vlage zraka.

## FOTOGALERIJA



## UPOZORENJA I MJERE OPREZA

Tehnički podaci i podaci o učincima navedeni u ovom dokumentu rezultat su laboratorijskog ispitivanja provedenog u kontroliranom okruženju te mogu pokazivati znatno drugačije rezultate od onih dobivenih pod drugačijim uvjetima na terenu. Nužno je provesti prethodne testove u stvarnim uvjetima primjene.

Korisnik je obavezan provjeriti Tehničke listove sa sigurnosnim podacima i obratiti pozornost na podatke o fizikalno-kemijskim svojstvima, zatim toksikološke podatke, upozorenja i druge korisne informacije kao one o sigurnom transport, uporabi i odlaganju proizvoda i ambalaže. U tekstu se također podsjeća da se proizvod i ambalaža ni u kom slučaju ne smije odlagati u okoliš.



Proizvodi i distribuira **AZICHEM srl**  
Via Giovanni Gentile, 16/A - 46044 Goito (MN), Italy  
Tel: +39 0376.604185 / 604365  
Fax: +39 0376 604398  
[www.azichem.com](http://www.azichem.com) - [info@azichem.com](mailto:info@azichem.com)

Ažurirano dana **24-06-2026**  
Uvjeti prodaje i pravne napomene dostupni na  
<https://www.azichem.com/opci-uvjeti-prodaje>  
**Ukupan broj stranica ovog dokumenta: 2**